



## Product Specifications

### SRW LS3 (Black, Non-Woven)

SRW LS3 is a superior quality, non-woven geotextile produced by needle punching together 100% polypropylene staple fibers in a random network to form a high strength dimensionally stable fabric. The polypropylene are specially formulated to resist ultraviolet light deterioration, and are inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. SRW LS3 conforms to the physical property values listed below:

Fabric Property	Test Method	Units	Minimum Average Roll Value
Weight (Typical)	ASTM D3776	oz/sy	3.5
Grab Tensile	ASTM D4632	lbs	115
Trapezoidal Tear	ASTM D4533	lbs	37
Puncture Resistance	ASTM D4833	lbs	54
Permittivity	ASTM D4491	1/sec	1.97
Water Flow (FH)	ASTM D4491	gal/min/ft <sup>2</sup>	182
AOS	ASTM D4751	US Sieve	50
UV Resistance (after 500hrs)	ASTM D4355	% strength retained	70

Roll Dimensions/Packaging (see catalog)

To the best of our knowledge, the information contained herein is accurate. However, SRW Products cannot anticipate all conditions under which SRW product information and our products or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of our products either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.